



environmental fact sheet

reflex

Australian Paper - Maryvale Paper Mill

Reflex Copy, Reflex Tints, Reflex 35% Recycled

Australian Paper - Burnie Paper Mill

Reflex Laser, Reflex Presentation

Thickness	ums	108	122	135
Grammage	gsm	80	90	100
Cobb 1min	g/cm ²	23	23	23
CIE Whiteness	UV Incl.	145	145	145
Moisture	%	4.7	4.7	4.7
Opacity	%	89.5	91.5	92.5
Roughness	Sheffield	170	170	170
Wax Pick	Wax Pick No.	18	18	18

Technical Capabilities

Printing Process Specifically designed for use through the full range of both high and low volume laser printers. Laser Guaranteed for 120+ sheets per minute.